

## Pallet Elastic Natural Rubber – Specifications

	Parameter	Test Method	Specifications
<b>Material Properties</b>	Modulus @ 300 % Elongation in psi (kg/cm <sup>2</sup> )	ISO 37	500 ± 70 (35.0 ± 5.0)
	Tensile Strength in psi (kg/cm <sup>2</sup> )	ISO 37	min. 2130 (min. 150.0)
	Elongation @ Break (%)	ISO 37	Min. 550.0
	Rubber Content (%)	In-House	Around 77
<b>Dimensional Properties</b>	Lay Flat Length (mm)	Measuring Tape	1244 ± 50.8
	Width (mm)	Vernier Caliper	25.4 ± 2.5
	Base Thickness @ center (mm)	Vernier Caliper	1.6 ± 0.2
	Thickness with Ridges @ center (mm)	Vernier Caliper	1.8 ± 0.2

### Cautions for use and storage:

- ➔ Stored in its original box in accordance with conditions recommended above a shelf life in excess of 4 years can be expected
- ➔ Avoid prolonged exposure to sunlight or contact with petroleum solvents and caustic chemicals
- ➔ Compliant with REACH, RoHS and POP directives

Article	Material	Colour	Issued date
Pallet Elastic	Rubber, 100 % Natural	Orange	28-11-2025